

IKO POLIMAR MC PRIMER

PRODUCT INFORMATION

A high performance two-part solvent based epoxy anti-corrosive primer for use on surfaces such as metal and concrete.

	Product Code
5L (3.6L Activator/1.4L Base)	PM70026A/B
15L (10.8L Activator/4.2L Base)	PM70027A/B

USE

Applied by brush or roller, the product is used for priming metal surfaces prior to the application of the **IKO Polimar Embedment Coat (EC)**.

The product must only be applied by operatives whom have successfully completed the IKO Polimar EC/UV product induction programme.

Additionally all work must be undertaken in accordance with the requirements of the specific information given with the IKO Specification document.

PERFORMANCE & COMPOSITION

Composition:	Epoxy
Form:	Liquid
Colour:	White
General Dimension Data	
Vessel Size:	5L/15L
Application Temperature	
Air:	
Surface:	
Coverage Rate at 20°C:	8.8m ² per/litre*
Drying Time	
Touch Dry:	4 Hours
Minimum Over coating:	16 Hours

* Dependent upon substrate

DIRECTIONS FOR USE

MATERIAL HANDLING

For specific storage and handling requirements, please refer to relevant sections of the IKO Material Safety Data Sheet.

SURFACE PREPARATION

All bare metal surfaces should be clean and prepared by abrading to a bright finish prior to applying **IKO Polimar MC Primer**.

APPLICATION

IKO Polimar MC Primer is a two part product; base and activator components must be thoroughly mixed together before use. Apply using a brush or roller at the specified coverage rate.

Allow the primer to dry fully before application of **IKO Polimar EC/UV**.

DISPOSAL

For specific disposal of waste, unused and contaminated packaging, please refer to relevant sections of the IKO Material Safety Data Sheet.

DISCLAIMER

As this product is utilised within an Approved Contractor network and guided by an IKO Specification document, where omission or differing information exists the IKO Specification document will take precedence.

Whilst every precaution is taken to ensure that the information given in this literature is correct and up to date it is not intended to form part of any contract or give rise to any collateral liability, which is hereby specifically excluded.

IKO reserve the right to amend and/or withdraw this document without notice. Intending purchasers of our materials should therefore verify with the company whether any changes in our specification, application details, withdrawals or otherwise have taken place since this literature was issued.