

IKOpro FLAT ROOF RENOVATOR

PRODUCT INFORMATION

IKOpro Flat Roof Renovator is a flexible bituminous coating containing reinforcing fibres and designed for easy application to protect and prolong the life of existing roofing systems.

	Product Code
2.5L	MW941500
5L	MW941600
22.5L	MW941622

USE

A bitumen fibre reinforced bitumen compound for the renovation of bitumen roof coverings.

FEATURES & BENEFITS

Ease of Use - brush application, straight from the tin.

PERFORMANCE & COMPOSITION

Composition:	Bitumen
Form:	Liquid
Colour:	Black
General Dimension Data	
Unit size:	2.5L/5L/22.5L
Coverage Rate*:	2.5m ² /litre/coat (0.4l/m ² /per coat)
Application Temperature:	
Surface	5°C and rising
Drying Times**:	24 hours

* Subject to surface porosity

** Depending upon external conditions

DIRECTIONS FOR USE

MATERIAL HANDLING

For specific storage and handling requirements, please refer to relevant sections of the IKO Safety Data Sheet.

SURFACE PREPARATION

All surfaces must be clean, dry and free from grease, oil, dirt and loose material. Treat any algae and fungi using IKOpro Algae and Fungi Remover as required, and prime the surface being treated with IKOpro Quick Drying Bitumen Primer.

Metal surfaces, where necessary, should be prepared with a wire brush. Iron and steel should be treated with a suitable rust inhibitive primer once prepared.

Any blisters and cracks present in the existing roof surface should be repaired using IKOpro Roof Repair Compound.

APPLICATION

Stir IKOpro Flat Roof Renovator thoroughly and then apply an even coating using a brush at a rate of 2.5m² per litre. Allow the product to dry thoroughly (approximately 24 hours).

Apply a second coat at right angles to the first at a rate of 2.5m² per litre, casting roof chippings into wet coating to provide UV protection to the renovated roof areas.

CLEANING

Brushes and tools can be cleaned with white spirit.

DISPOSAL

For specific disposal of waste, unused and contaminated packaging, please refer to relevant sections of the IKO Safety Data Sheet.

DISCLAIMER

Whilst every precaution is taken to ensure that the information given in this literature is correct and up to date it is not intended to form part of any contract or give rise to any collateral liability, which is hereby specifically excluded.

IKO reserve the right to amend and/or withdraw this document without notice. Intending purchasers of our materials should therefore verify with the company whether any changes in our specification, application details, withdrawals or otherwise have taken place since this literature was issued.